

Veradel® 3600P

polyethersulfone

Veradel® PESU was formerly marketed as Gafone™ PESU

Veradel® 3000P, 3100P, 3200P, 3400P and 3600P are polyethersulfone (PESU) powders for dissolving or dispersing into solutions. They can also be ground to smaller particle size or blended with other solid particles. The grades differ by their molecular weights, with 3000P the highest and 3600P the lowest. There is a direct correlation between molecular weight and solution viscosity.

PESU offers excellent toughness and outstanding hydrolytic resistance. It resists attack from steam, boiling water, and

mineral acids. Cast films or coatings of PESU are transparent and have additional desirable properties including long term thermal stability, excellent metal adhesion and formability and inherent flame resistance.

Typical applications include high-temperature coating formulations, membranes, advanced high-temperature composites, and specialty adhesives.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Acid Resistant • Flame Retardant • Food Contact Acceptable • Good Adhesion • Good Chemical Resistance	• Good Creep Resistance • Good Dimensional Stability • Good Thermal Stability • Good Toughness • High Flow	• High Heat Resistance • High Tensile Strength • Hydrolysis Resistant • Low Molecular Weight • Medium Rigidity
Uses	• Adhesives • Binder	• Coating Applications • Compounding	
Agency Ratings	• NSF 51 ¹		
RoHS Compliance	• RoHS Compliant		
Appearance	• Transparent - Slight Yellow		
Forms	• Granules	• Powder	
Processing Method	• Coating	• Solution Processing	• Spraying

Physical	Typical Value	Unit	Test method
Specific Gravity	1.37		ASTM D792
Water Absorption (24 hr)	0.60	%	ASTM D570
Solution Viscosity ²	275	mPa·s	Internal Method
Residual Solvent	0.50	%	Internal Method

Thermal	Typical Value	Unit	Test method
Glass Transition Temperature	220	°C	ASTM E1356
CLTE - Flow	4.9E-5	cm/cm/°C	ASTM D696

Veradel® 3600P

polyethersulfone

Notes

Typical properties: these are not to be construed as specifications.

¹ Maximum Temperature of Use: 124°C (356°F)

² 25% in dimethylacetamide at 40°C

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa

SpecialtyPolymers.Americas@solvay.com | Americas

SpecialtyPolymers.Asia@solvay.com | Asia and Australia

Safety Data Sheets (SDS) are available by emailing us or contacting your sales representative. Always consult the appropriate SDS before using any of our products.

Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right.

All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.

© 2014 Solvay Specialty Polymers. All rights reserved.

